



Roflam Series

Flame retardants
for one component foam

Features

- Liquid form
- Low viscosity
- Very low acid number
- Non-reactive
- Water-free

Advantages

- Good flammability performance
- Efficient viscosity reduction
- Easily processed in PU foaming
- Unchanged mechanical performance of PU foams

Typical properties

Product name	Chemical name	Appearance	Viscosity (at 25°C)	Density (at 25°C)	Phosphorus content	Chlorine content	Water content
		visual method	EN ISO 12058	EN ISO 2811	based on composition (GC-MS analysis)	based on composition (GC-MS analysis)	ISO 760
		—	mPa·s	g/cm³	% (w/w)	% (w/w)	% (w/w)
Roflam P (High Efficiency)	tris(2-chloro-1-methylethyl) phosphate	transparent, colourless to slightly yellow liquid	66	1.28	9.5%	32.5	< 0.1
Roflam B7 (Halogen free)	tert-butylphenyl-phenyl phosphate		72	1.18	8.5%	–	< 0.1
Roflam B7L (Halogen free)			310	1.12	7.4%	–	< 0.1

Product performance

Foam properties	Form. 1		Form. 2		Form. 3	
	Roflam P	14.7%*	Roflam B7	14.7%*	Roflam B7L	17.0 %*
Fire test DIN 4102, class B2 / EN 13501-1, class E	pass		pass		pass	
Fire test ISO 4589-2, Limited Oxygen Index	23.3%		21.5%		21.6%	
Compression strength, 168h	26.9 kPa		34.1 kPa		38.5 kPa	
Shrinkage wet Max After 336h	-8.5% 3.4%		-4.1% -1.1%		-0.4% -0.1%	
Shrinkage dry Max After 336h	2.8% 2.9%		1.2% 1.8%		0.0% 0.0%	
Yield in mould 600g 750g	33.3 L 41.6 L		29.5 L 36.9 L		32.8 L 40.1 L	
Post expansion	105%		106%		106%	

* amount per net mass of foam